

PP-2150-MFill3

Polypropylene Compound Reinforced with Glass Fiber

Injection Grade



Technical Data Sheet

Product Description

PP-2150-MFill3 is Homo-polymer Polypropylene based Compound in natural color reinforced with 30% of Chopped Glass Fiber. This grade has good mechanical properties, impact resistance, thermal properties and dimensional stability. It is designed for use in a wide range of injection parts especially in automotive industry.

General

Material Status: Available
Processing Method: injection molding
Form: Pellet
Color: Black

Properties

Properties	Nominal Value	Test Method
Density	1.12 g/cm ³ (±0.01)	ASTM D792
MFI (230°C/ 2.16kg)	5 g/10 min (±1)	ASTM D1238
Izod Impact, Notched	9 kJ/m ² (±1)	ISO 180
Tensile Strength at Yield	75 MPa (±5)	ASTM D638
Elongation at Break	4% (±1)	ASTM D638
Elastic Modulus	4000 MPa (±200)	ASTM D638
Heat Deflection Temperature (0.45MPa)	165 °C (±5)	ASTM D648

Typical Properties: These values are not to be considered as product specifications

For more details please contact us

www.modiranpolymer.com